

MastaLine

JOINTING COMPOUND



TECH DATA

MastaLine is a premixed jointing compound formulated to perform in all phases of jointing, coating trim and fasteners and final coating.

MastaLine can also be applied as a final coat over MastaBase, MastaLongset or MastaTape Universal.



Performance

Body

Good for both hand and mechanical tools.

Drying

Convenient drying time to obtain thin edges when feathering as it does not dry out too fast.

Colour

Light colour when applied, drying to a white finish.

Sanding

Can be sanded by hand or by electric sanders. Leaves a professional finish.

Sustainable

Low VOC meeting sustainable building project requirements.

Benefits

- > All purpose
- > Premixed for easy use

Product Information

SIZE	23.4kg bucket		
TYPE	Mid weight air drying premixed all purpose compound		
DRYING TIME	24 - 48 hours under normal drying conditions		
SYSTEM USAGE	<input checked="" type="checkbox"/> Bedding	<input checked="" type="checkbox"/> Second coat	<input checked="" type="checkbox"/> Final coat
	<input checked="" type="checkbox"/> Standard		
VOC	<50g/L as VOC content per coating		
SPECIFIC DENSITY	1.2g/cc		

TECH DATA

Application

- Test for desired consistency depending on application method to be used. MastaLine is ready to use for hand trowelling. For mechanical tools, if necessary add clean tap water in small amounts and mix until desired consistency is achieved.
- If mixing MastaLine, note that overmixing may introduce air bubbles.
- As with all compounds, excessive thinning may cause cracking or increased shrinkage. Do not mix with any other material.
- Maintain a minimum 13°C working temperature during application and drying.
- When using MastaLine for all three coats, joints must be back-blocked. MastaMate Paper Tape is recommended for use with MastaLine.
- For a stronger joint, use MastaMate Paper Tape and bedding cement for the first two coats, with MastaLine as the final coat.

- Allow MastaLine to dry completely between coats and approximately 24 - 48 hours before sanding.
- Sand lightly by hand using 150 grit paper or 180 sanding mesh. When using an electric sander use 220 grit paper.
- MastaLine will accept most types of decorative finishes. In accordance with AS/NZS 2311 *Guide to the painting of buildings*, a three coat paint system must be used. This consists of a sealer/undercoat and two coats of paint.

Optimise product performance by:

- Firmly closing the lid to prevent the compound from drying out.
- Washing tools before product dries and hardens.
- Storing in a dry, well ventilated environment fully protected from the weather.



Warranty

Knauf's products are guaranteed by a 10 Year Warranty. For details visit

knaufplasterboard.com.au
knaufplasterboard.co.nz

Technical Advice

AU **1300 724 505**
NZ **0800 884 326**